

## SECTION 58

**PRESERVATIVE TREATMENT OF LUMBER, TIMBER AND PILING**

Preservative treatment of lumber, timber, and piling shall conform to Section 58 of the Caltrans Standard Specifications and these City Standard Specifications.

**58-1.02 Treatment and Retention.** - When lumber, timber, or piling is treated with fluor chrome arsenate phenol, the retention shall be at least 0.50 pound per cubic foot.